

(19) World Intellectual Property Organization  
• International Bureau



(43) International Publication Date  
3 January 2002 (03.01.2002)

PCT

(10) International Publication Number  
**WO 02/00787 A1**

(51) International Patent Classification<sup>7</sup>: **C08L 53/02**,  
C08F 297/04, C09D 5/00, E01F 9/04, 9/08

(21) International Application Number: PCT/US01/20289

(22) International Filing Date: 25 June 2001 (25.06.2001)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:  
09/603,530 27 June 2000 (27.06.2000) US  
09/605,032 27 June 2000 (27.06.2000) US

(71) Applicant (for all designated States except US): **EXXON-MOBIL CHEMICAL COMPANY** [US/US]; 5200 Bayway Drive, Baytown, TX 77520-5200 (US).

(72) Inventors; and

(75) Inventors/Applicants (for US only): **DELME, Roger**,

**Robert** [BE/BE]; Nieuwe Baan 7, B-1674 Bellingen (BE). **LECHAT, Jacques, Bernard** [FR/FR]; Avenue Lord Byron 2, B-1410 Waterloo (BE). **MARTIN, Chantal, Mathilde** [BE/BE]; Baty Godin, 5, B-1471 Loupoigne (BE).

(74) Agents: **RUNYAN, Charles, E.** et al.; ExxonMobil Chemical Company, P.O. Box 2149, Baytown, TX 77522-2149 (US).

(81) Designated States (*national*): BR, CN, JP, MX, US.

(84) Designated States (*regional*): European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, TR).

Published:

— with international search report

*For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.*

(54) Title: **TETRABLOCK COPOLYMERS**

(57) Abstract: This invention relates generally to linear tetrablock copolymer compositions and their use in road-marking applications. These tetrablock copolymers contain polystyrene, polyisoprene and polybutadiene components. Road-marking compounds prepared from these copolymers further contain a hydrocarbon resin or rosin ester or both. These block copolymer are readily mixed using melt-mixing techniques, thus, avoiding both powder grinding and high-shear stirring.

**WO 02/00787 A1**

**TITLE: TETRABLOCK COPOLYMERS****FIELD**

5 This invention relates generally to linear tetrablock copolymer compositions and their use in road-marking applications. These tetrablock copolymers contain polystyrene, polyisoprene and polybutadiene components. Road-marking compounds prepared from these copolymers typically further contain hydrocarbon resin, fillers and glass beads.

**BACKGROUND**

10 Block copolymers are generally known in the art and have been used in a variety of applications. There are two basic, distinct block copolymer types: linear and radial.

15 Radial block copolymers contain polymer block branches radiating from a central coupling agent. Such polymers are described in, for example, U.S. Patent No. 5,399,627. This patent describes polymers for use in pressure sensitive adhesive compositions and describes radial block copolymers comprised of polystyrene, polyisoprene, and polybutadiene block segments.

20 Linear block copolymers do not have radiating branches; the block components are arranged sequentially. For example, U.S. Patent No. 5,750,623 describes linear styrene-isoprene-styrene and styrene-butadiene-styrene block copolymers useful in hot-melt adhesives.

25 Linear block copolymers are also used to prepare compositions for road or pavement marking. Such compositions typically comprise copolymer elastomer and hydrocarbon resin components as well as color and reflective additives such as pigments and glass beads.

30 U.S. Patent No. 5,213,439 is directed to pavement marking and describes a dry-blended powder containing linear or radial tri-block copolymers with two poly(vinylaromatic) blocks and a conjugated diene block. This copolymer must be ground to a powder before mixing with hydrocarbon resins and other additives. This grinding replaces prolonged melt-blending procedures using expensive high-shear stirring to mix thermoplastic rubbers with hydrocarbon resin.

We have discovered that certain linear tetrablock copolymer compositions are readily melted and mixed with hydrocarbon resin thus avoiding both powder grinding and high-shear stirring. Such copolymers have potential value in road-marking applications in addition to their more typical adhesive applications.

5

### SUMMARY

The present invention relates to a tetrablock copolymer composition comprising a linear SISI of SISB block copolymer. The block copolymers are of styrene and isoprene and/or butadiene. The styrene content of the polymers used in the present invention should be from 10–27 percent by weight, alternatively  
10 from 12–20 or 15–18 percent by weight.

Molecular weights are measured by Gel Permeation Chromatography (GPC), where the GPC system has been appropriately calibrated for example by using standards of similar known-molecular-weight polymer.

Accordingly, the present invention selects polymers that enable good  
15 melting when mixed in traditional thermoplastic road-marking mixers. Some polymer embodiments have the following properties: an overall styrene content between 10–27 wt%, alternatively between 12–20 wt%. The preferred rubbers are 100% tetrablock.

20 The styrenic block copolymers used in some invention embodiments have a molecular weight of from 45,000–250,000. The molecular weights of the various copolymer blocks may be varied. Some embodiments select the styrenic blocks with a molecular weight of from 4,000–35,000, alternatively, 6,000–20,000 or 8,000–20,000.

25 The unsaturated diene blocks should have a molecular weight of from 10,000–200,000, alternatively, 10,000–150,000 or 10,000–50,000 which is particularly preferred with isoprene blocks. Unsaturated diene blocks with molecular weights of 20,000 or above provide a suitably strong polymer. Unsaturated diene blocks with molecular weights of 200,000 or less are suitably  
30 processable. Where SISI, SISB, SBSI, or SBSB polymers are used, the molecular weight of the two unsaturated diene blocks can be varied.

**DETAILED DESCRIPTION**

This invention's linear tetrablock copolymers are particularly useful in road-marking compounds due to their flowability and quick melting capability. They can easily be melt mixed with hydrocarbon resins and other additives without powdering or high-shear mixing. Each block may be either polystyrene (S), polybutadiene (B), or polyisoprene (I). Since there must be four blocks, one of the blocks will be repeated. In some embodiments, the tetrablock copolymer contains two S blocks plus two B blocks, two I blocks, or one B and one I block, i.e.: S-I-S-I, S-I-S-B, S-B-S-B and S-B-S-I.

Each block is present at 10–90 wt% of block copolymer based on the total copolymer weight. In some embodiments, an S component exists in a tetrablock copolymer at a minimum of 5 wt%, alternatively, a minimum of 10 wt%. The S component exists at up to 70 wt%, alternatively up to 60 wt%, up to 40 or up to 30 wt% of the copolymer.

The weight-average molecular weight of invention tetrablock copolymers varies widely depending on the copolymer's make-up. Generally, the overall peak weight-average molecular weight has a minimum of 10,000, alternatively, a minimum of 50,000, or 100,000. The overall peak weight-average molecular weight maximum is 1,000,000, alternatively not more than 500,000, not more than 300,000, or not more than 200,000.

In some embodiments, the invention linear tetrablock copolymers are "pure" in the sense that they contain no measurable residual triblock or diblock copolymer. But they may contain up to 1% by weight residual triblock and/or diblock copolymer.

For road-marking application, these linear tetrablock copolymers are mixed with a hydrocarbon resin, such as a substantially non-aromatic hydrocarbon resin, or with a rosin ester or a blend of both. Substantially non-aromatic means that if there is aromatic hydrocarbon present, it is at a low enough level to function in these copolymer compositions. Preferred non-aromatic resins are polymerized from a stream of aliphatic petroleum derivatives in the form of dienes and mono-olefins containing 5 to 6 carbon atoms. At room temperature, these hydrocarbons range from materials that are normally liquid to those that are normally solid at

room temperature. Commercially available resins, such as ESCOREZ™ 1102RM (ExxonMobil Chemical), are suitable. Many useful resins have a Ring and Ball softening point (ASTM D 28-96) from 90–110°C, alternatively from 95–105°C, and a melt viscosity at 160°C (ETM-E-31) from 500–3000 mPa sec, alternatively from 1000–2500 mPa sec. Suitable hydrocarbon resins are well known and commercially available, e.g. under the trademarks "ESCOREZ™", "HERCULES™", "QUINTONE™". Suitable rosin esters are commercially available, e.g. under the trademarks "BEVILINE™" and "SYLVATAC™".

The relative amounts of tetrablock copolymer and hydrocarbon resin depends on the selected components. Typically, the block copolymer and hydrocarbon resin are present in a weight ratio of from 0.5:99.5 to 20:80, preferably from 2:98 to 15:85.

Invention road-marking compositions may further contain additives such as pigments, glass beads, fillers, oils, and viscosity modifiers. Titanium dioxide is a particularly useful pigment, and mineral aggregates are particularly useful fillers.

The compositions' individual components may be combined in a number of ways, but the invention copolymers are uniquely suited to simple melt mixing with the hydrocarbon resin and any desired additive. Typically, the melt-mixing temperature has a minimum of 170°C or 180°C. Typically, the maximum melt-mixing temperature is 200°C, but melt-mixing temperatures as high as 210°C are not unusual.

The tetrablock copolymers may be prepared by any suitable polymerization technique. Polymerization systems in which the blocks are produced sequentially are preferred to those in which two or more pre-formed blocks are coupled to each other. The preferred, sequential, polymer development enables greater variation in the molecular weight of the blocks.

### EXAMPLES

The following examples are intended to illustrate the melt behavior of invention tetrablock copolymers as compared to triblock and diblock copolymers. The samples were placed in an oven at 190 °C for 5 and 10 minutes. Faster

melting and higher flowability indicate that the polymer will be easier to mix for road-marking applications.

The molecular weights reported here are peak molecular weight as measured by size exclusion chromatography using polystyrene calibration. Commercially available polystyrene standards were used for calibration, and the molecular weights of copolymers corrected according to Runyon et al, *Journal of Applied Polymer Science*, Vol. 13, Page 359 (1969) and Tung, L. H., *Journal of Applied Polymer Science*, Vol. 24, Page 953 (1979).

Typically, the melt-mixing temperature has a minimum of 170 °C or 180 °C. The maximum melt-mixing temperature is usually 200 °C, but melt-mixing temperatures as high as 210 °C are not unusual.

Melt flow rate (MFR) was determined using ASTM D 1238, 200/5.0.

Comparative Sample 1 is an S-I-S triblock copolymer, VECTOR™ 4111 (commercially available from Dexco Polymers).

Comparative Sample 2 is an S-I-S/S-I triblock/diblock copolymer mix, VECTOR™ 4113 (commercially available from Dexco Polymers).

Comparative Sample 3 is an S-I-S/S-I triblock/diblock copolymer mix, VECTOR™ 4114 (commercially available from Dexco Polymers).

Comparative Sample 4 is an S-I-S/S-I triblock/diblock copolymer mix, DPX 559™, (commercially available from Dexco Polymers) having 15% styrene, 55% SI and a Melt Flow Rate (condition G) of 44 g/ 10 min.

Comparative Sample 5 is an S-I-S triblock copolymer, DPX 562™ (commercially available from Dexco Polymers). DPX 562™ is a linear SIS with 15% styrene and a Melt Flow Rate (ASTM 1238, 200/5.0) of 25 g/10 min.

Comparative Sample 6 is an S-I-S/S-I triblock/diblock copolymer mix, DPX 565™ (commercially available from Dexco Polymers). DPX 565™ has the following properties. Molecular weight SIS: 176000 g/mol; Molecular weight SI: 83000 g/mol; Styrene content SIS: 16.1% (by weight); Styrene content SI: 16.1% (by weight); SI content: 54% of the polymer.

Invention Sample 7 is an S-I-S-I tetrablock copolymer in accordance with this invention made at Dexco Polymers by sequential polymerization. It has the

following respective molecular weights, in g/mol: 12400, 60000, 12400, 70000, and styrene content of 16% (by weight).

Invention Sample 8 is an invention S-I-S-B tetrablock copolymer made at Dexco Polymers by sequential polymerization. It has the following respective molecular weights, in g/mol: 11000, 57000, 11000, 40000, and styrene content of 19% (by weight).

Comparative Sample 9 is an S-I-S/S-I triblock/diblock copolymer mix, TR 1107™ (commercially available from Shell Oil Company).

Comparative Sample 10 is an S-I-S/S-I triblock/diblock copolymer mix, KRATON™ D 601 P (commercially available from Shell Oil Company).

Comparative Sample 11 is an S-I-S/S-I triblock/diblock copolymer mix, KRATON™ D 113 (commercially available from Shell Oil Company).

Comparative Sample 12 is an S-I-S/S-I triblock/diblock copolymer mix, QUINTAC™ 3433 (commercially available from Nippon Zeon).

Table 1

Sample	Melt Rating @ 5 min.*	Melt Rating @ 10 min.	% Styrene	% Diblock	MFR	MW
Comp.1	1	2	18	0	12	118000
Comp 2	2	4	15	18	10	154000
Comp 3	2	4	18	42	25	156000
Comp 4	2	5	15	58	37	162000
Comp 5	2	5	15	0	25	n/a
Comp 6	1	2	16	54	12	176000
Inv. 7	2	5	16	0		154000
Inv. 8	4	5	19	0		126000
Comp 9	2	4	15	17	9	n/a
Comp 10	3	4	15	19	12	n/a
Comp 11	2	4	16	56	16	168000
Comp 12	2	4	17	55	12	172000

\*1= no change in sample; 2=sample slightly melted; 3=sample completely melted, no flow;  
4=sample completely melted, limited flow; 5=sample completely melted good flow.

While certain representative embodiments and details have been provided to illustrate the invention, it will be apparent to skilled artisans that various process and product changes from those disclosed in this specification may be made without departing from this invention's scope, which the appended claims define. These are within the scope of the invention. Furthermore, certain features or elements are described in the disclosure (i.e. specification and claims as filed).

All combinations of these elements or features are within the invention's scope to the extent that the combinations do not conflict with the disclosure taken as a whole.

5 All patents, test procedures, and other documents cited in this specification are fully incorporated by reference to the extent that this material is consistent with this specification and for all jurisdictions in which such incorporation is permitted.

All documents to which priority is claimed are fully incorporated by reference for all jurisdictions in which such incorporation is permitted.

10 Certain invention features are described as numerical ranges or upper limits or lower limits. The invention specifically encompasses values of those features that fall between any of the specifically mentioned upper or lower limits unless otherwise indicated.

15 The specification and claims as filed disclose different aspects of the invention. The individual components or elements may be combined in any novel combination, regardless of whether the claims recite each individual combination, and remain within Applicants' intended disclosure.



CLAIMS

1. A road-marking compound comprising:
  - (a) at least one linear tetrablock copolymer having four blocks independently selected from polystyrene (S), polyisoprene (I) and polybutadiene (B); and
  - (b) at least one of hydrocarbon resin, rosin ester, or a mixture of rosin ester and hydrocarbon resin.
2. The road-marking compound of claim 1 wherein two of the blocks are the same and are one of polystyrene (S), polyisoprene (I), or polybutadiene (B).
3. The road-marking compound of claim 1 wherein the tetrablock copolymer is represented by the formula S-I-S-B, S-I-S-I, S-B-S-B or S-B-S-I wherein S is polystyrene, I is polyisoprene, and B is polybutadiene.
4. The road-marking compound of claim 3 wherein each of the four blocks is present in the amount of 10–90% wt% based on the total copolymer weight.
5. The road-marking compound of claim 4 wherein the copolymer's overall peak weight-average molecular weight ranges from 10,000–1,000,000.
6. The road-marking compound of claims 1-5 wherein the copolymer contains less than 1 wt% residual diblock.
7. The road-marking compound of claims 1-5 wherein the copolymer contains less than 1 wt% residual triblock.

8. The road-marking compound of claims 1-5 wherein the copolymer contains less than 1 wt% residual S-I diblock and less than 1 wt% residual S-I-S triblock.

5 9. The road-marking compound of claim 8 wherein the total residual S-I diblock and S-I-S triblock copolymer is less than 1 wt%.

10. The road-marking compound of claims 1-5 or 8 wherein the hydrocarbon resin is substantially non-aromatic.

10

11. The road-marking compound of claims 1-5 or 10 wherein the hydrocarbon resin viscosity is from 0.1–10 Pa sec at 160 °C.

15

12. The road-marking compound of claims 1-5, 8, 10, or 11 wherein the hydrocarbon resin softening temperature is at least 90°C.

13. The road-marking compound of claims 1-5, 8, 10, or 12 wherein the copolymer and hydrocarbon resin are present in a weight ratio of from 0.5:99.5 to 20:80.

20

14. A road-marking compound comprising:

- (a) a linear tetrablock copolymer represented by the formula S-I-S-B, S-I-S-I, S-B-S-B or S-B-S-I wherein S is a polystyrene component, I is a polyisoprene component, and B is polybutadiene component; wherein each copolymer component is present in the amount of 10–90% wt% based on the total copolymer weight; the overall peak, weight-average molecular weight of the copolymer ranges from 10,000–1,000,000; and the copolymer contains less than 10 wt% residual S-I diblock and less than 10 wt% residual S-I-S triblock ; and

25

30

- (b) a substantially non-aromatic hydrocarbon, having a viscosity ranging from 0.1–10 Pa sec, a wax cloud point of up to 190°C, and a softening point that is at least 90°C;

wherein the copolymer and hydrocarbon resin are present in a weight ratio of from 0.5:99.5 to 20:80.

15. A tetrablock copolymer composition comprising a linear block copolymer represented by the formula S-I-S-B wherein the S component is polystyrene, the I component is polyisoprene and the B component is polybutadiene.

16. The copolymer of claim 15 wherein the S component is present in the amount of 10–90 wt% of the block copolymer based on the total weight of the block copolymer.

17. The copolymer of claim 15 wherein the I component is present in the amount of 10–90 wt% of the block copolymer based on the total weight of the block copolymer.

18. The copolymer of claims 15-17 wherein the B component is present in the amount of 10–90 wt% of the block copolymer based on the total weight of the block copolymer.

19. The copolymer of claim 18 wherein

- (a) the S component is present in the amount of 10–90 wt% of the block copolymer based on the total weight of the block copolymer;
- (b) the I component is present in the amount of 10–90 wt% of the block copolymer based on the total weight of the block copolymer, and
- (c) the B component is present in the amount of 10–90 wt% of the block copolymer based on the total weight of the block copolymer.

20. The copolymer of claim 19 wherein the overall, peak weight-average molecular weight of the copolymer is 10,000–1,000,000.
- 5 21. The copolymer of claim 20 wherein the copolymer contains less than 10 wt% residual S-I diblock.
22. The copolymer of claim 21 wherein the copolymer contains less than 10 wt% residual S-I-S triblock.
- 10 23. The copolymer of claim 22 wherein the copolymer contains less than 10 wt% residual S-I diblock and less than 10 wt% residual S-I-S triblock.
24. The copolymer of claim 15 wherein the copolymer contains less than 10 wt% residual S-B diblock.
- 15 25. A tetrablock copolymer composition comprising:
- (a) A linear block copolymer represented by the formula S-I-S-B wherein
- 20 (i) the S component is polystyrene and is present at 10–90 wt% based on the total copolymer weight,
- (ii) the I component is polyisoprene and is present at 10–90 wt% based on the total copolymer weight, and
- (iii) the B component is polybutadiene and is present at 10–90 wt% based on the total copolymer weight
- 25 wherein the overall peak weight-average molecular weight of the copolymer ranges from 200,000–1,000,000; and the copolymer contains less than 10 wt% residual S-I diblock, less than 10 wt% residual S-I-S triblock, and less than 10 wt% residual S-B diblock.
- 30 26. A method of using any of the road-marking compounds of Claims 34–46 comprising supplying the tetrablock copolymer.

## INTERNATIONAL SEARCH REPORT

International Application No.

PCT/US 01/20289

## A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 C08L53/02 C08F297/04 C09D5/00 E01F9/04 E01F9/08

According to International Patent Classification (IPC) or to both national classification and IPC

## B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 C08L C09D C09J E01F C08F

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the International search (name of data base and, where practical, search terms used)

EPO-Internal, WPI Data, PAJ

## C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	EP 0 499 326 A (SHELL INT RESEARCH) 19 August 1992 (1992-08-19) * claims 1-19 ; abstract ; page 3, line 40 - page 4, line 13 ; page 2, line 1-10* page 5, line 1-49	1-26
X	US 5 627 235 A (HIMES GLENN R) 6 May 1997 (1997-05-06) * column 9, line 18 ; abstract * column 7, line 26 -column 8, line 16; claims 1-3	1-26
P,X	WO 00 56796 A (BRIDGESTONE FIRESTONE INC) 28 September 2000 (2000-09-28) * claims 1-3 ; page 8, line 25-26 * page 5, line 8 -page 6, line 21 -/-	1-14



Further documents are listed in the continuation of box C.



Patent family members are listed in annex.

## \* Special categories of cited documents :

\*A\* document defining the general state of the art which is not considered to be of particular relevance

\*E\* earlier document but published on or after the international filing date

\*L\* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

\*O\* document referring to an oral disclosure, use, exhibition or other means

\*P\* document published prior to the international filing date but later than the priority date claimed

\*T\* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

\*X\* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

\*Y\* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

\*G\* document member of the same patent family

Date of the actual completion of the international search

1 October 2001

Date of mailing of the international search report

11/10/2001

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2  
NL - 2280 HV Rijswijk  
Tel (+31-70) 340-2040, Tx. 31 651 epo nl,  
Fax: (+31-70) 340-3016

Authorized officer

Hammond, A

## INTERNATIONAL SEARCH REPORT

International Application No

PCT/US 01/20289

## C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	GB 2 289 681 A (NISSIN KASEI CO LIMITED) 29 November 1995 (1995-11-29) * page 1, line 1-9 ; page 4, line 23 - page 5, line 7 ; page 2, line 3 - page 3, line 22 * page 5, line 33 ---	1-26
Y	GB 2 226 322 A (ENICHEM ELASTOMERS) 27 June 1990 (1990-06-27) claims 1-14 ---	1-26
A	WO 97 09385 A (EXXON CHEMICAL PATENTS INC ;DELME ROGER (BE)) 13 March 1997 (1997-03-13) * claims 1-11 ; page 3, line 10-17 * page 5, line 12 -page 6, line 13 ---	1-26
A	US 4 168 286 A (MOCZYGEMBA GEORGE A) 18 September 1979 (1979-09-18) * abstract ; claims 1-22 * column 6, line 33-36 ---	1-26
A	US 4 161 472 A (LEHR MARVIN H) 17 July 1979 (1979-07-17) * column 7, line 48 - column 8, line 3 * column 1, line 19-23 -----	1-26

## INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/US 01/20289

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP 0499326	A	19-08-1992	AT 140471 T 15-08-1996
			BR 9200476 A 20-10-1992
			CA 2061284 A1 15-08-1992
			DE 69212174 D1 22-08-1996
			DE 69212174 T2 12-12-1996
			DK 499326 T3 12-08-1996
			EP 0499326 A1 19-08-1992
			FI 920596 A 15-08-1992
			JP 4318084 A 09-11-1992
			KR 254104 B1 15-04-2000
			NO 303642 B1 10-08-1998
			RU 2089584 C1 10-09-1997
			US 5213439 A 25-05-1993
US 5627235	A	06-05-1997	US 5589542 A 31-12-1996
			AT 163031 T 15-02-1998
			AU 687131 B2 19-02-1998
			AU 1107395 A 23-05-1995
			BR 9407936 A 26-11-1996
			CN 1136821 A ,B 27-11-1996
			DE 69408474 D1 12-03-1998
			DE 69408474 T2 04-06-1998
			DK 726927 T3 11-05-1998
			WO 9512645 A1 11-05-1995
			EP 0726927 A1 21-08-1996
			ES 2111966 T3 16-03-1998
			JP 9504566 T 06-05-1997
			NO 961760 A 28-06-1996
			US RE36757 E 27-06-2000
WO 0056796	A	28-09-2000	WO 0056796 A1 28-09-2000
GB 2289681	A	29-11-1995	NONE
GB 2226322	A	27-06-1990	BE 1003108 A3 26-11-1991
			BR 8906764 A 18-09-1990
			CA 2005285 A1 23-06-1990
			CN 1043512 A ,B 04-07-1990
			CN 1158866 A ,B 10-09-1997
			DE 3942668 A1 28-06-1990
			DK 623289 A 24-06-1990
			ES 2021927 A6 16-11-1991
			FR 2640979 A1 29-06-1990
			MX 169895 B 29-07-1993
			NL 8903136 A 16-07-1990
			NO 177599 B 10-07-1995
			NO 950562 A 25-06-1990
			SE 502757 C2 08-01-1996
			SE 8904152 A 24-06-1990
			US 5284915 A 08-02-1994
			US 5304598 A 19-04-1994
WO 9709385	A	13-03-1997	DE 69613847 D1 16-08-2001
			WO 9709385 A1 13-03-1997
			EP 0850276 A1 01-07-1998
US 4168286	A	18-09-1979	NONE

# INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/US 01/20289

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
---	---------------------	----------------------------	---------------------

US 4161472	A	17-07-1979	NONE
------------	---	------------	------